



Esstech, Inc.
48 Powhattan Avenue,
Essington, PA 19029
P: 610-521-3800
F: 610-521-4600
www.esstechinc.com
sales@esstechinc.com

Item # X-851-1066, Urethane Dimethacrylate IPDI

Product Name: Isophorone Urethane Dimethacrylate, UDMA-IPDI

UDMA-IPDI has a higher viscosity than our X-850-0000, urethane dimethacrylate. The high molecular weight of X-851-1066 results in lower polymerization shrinkage when cured.

TYPICAL PROPERTIES

Molecular Formula	Proprietary
Molecular Weight	Proprietary
Refractive Index	1.4938
Viscosity @ 25°C (cps)	100,000 – 500,000
Color (APHA)	<50
Inhibitor	BHT – 300-700 ppm, MeHQ - <35 ppm