

Item # X-892-0000, Exothane 26

Product Name: Exothane 26

The homopolymer of Exothane 26 has the unique ability to re-adhere to itself at lower tensile strength. Exothane 26 exhibits high flexibility when cured.

TYPICAL PROPERTIES

| | |
|---------------------------------------|-----------------|
| Molecular Formula | Proprietary |
| Molecular Weight | Proprietary |
| Refractive Index | 1.4766 |
| Inhibitor | BHT – 586 ppm |
| Toxic Substance Control Act List | Listed |
| Toughness at Max Strength (J) | 1.3 |
| Conversion (%) | 96.2 |
| Volumetric Shrinkage (%) | 3.6 |
| Average Shrinkage Stress (MPa) | 0.1 |
| Color (APHA) | 24 |
| Avg. Hardness | 53 |
| Max Strength (N) | 124.7 |
| Tensile Strength (N/mm ²) | 5.9 |
| Modulus (GPa) | 0.017 |
| Elongation (%) | 45.69 |
| Viscosity @ 40°C (cps) | 12,269 – 17,200 |